



TECHNICAL BULLETIN

REBOUND CRICKET WICKET

ARCHITECT SPECIFICATION DETAIL

1. Base Works

For details of base works suitable for **Rebound Ace Sports** installation, see separate technical bulletin titled 'Base Construction Specification' for construction of concrete or asphalt bases.

- 1.1 **Concrete** New concrete shall be allowed to cure for a minimum of 28 days.

The concrete base is to be waterproof. This means that water should not be allowed to enter the concrete base from below or from the side. Special care is needed on slabs installed on 'cut and fill' sites and in areas of high water table.

- 1.2 **Asphalt** New asphalt shall be allowed to oxidise for a period of 14-21 days depending on climatic conditions.

2. Surface Preparation

2.1 **Surface Accuracy**

Base surface shall be laid to an accuracy of a maximum deviation of 3mm beneath a 3 metre straight edge when measured in any direction.

2.2 **Concrete**

Ensure concrete surface is free from all dust, dirt, grease, etc. Concrete is to be etched with a mixture of 4 parts **Water** to 1 part **Hydrochloric Acid** and thoroughly rinsed with clean water under pressure to ensure removal of all laitance and cement slurry. Concrete must be thoroughly dry before application of **Rebound Cricket Wicket**.

2.3 **Asphalt**

Asphalt shall be free from all dust, dirt, grease, etc. If necessary, asphalt shall be cleaned by high pressure water blasting and is to be thoroughly dry before application of **Rebound Cricket Wicket**.

3. Surfacing System

Rebound Cricket Wicket is a water impermeable polyurethane/rubber/acrylic composite surface laid in mats at a minimum total thickness of 5mm.

Surface composition consists of:

HEAD OFFICE: QUEENSLAND 15-21 Argon Street, Carole Park, Queensland 4300, Australia

☎ +61 7 37238800 Fax + 617 32714659

Email info@reboundace.com.au

www.reboundace.com.au



TECHNICAL BULLETIN

- 3.1 **Rebound Adhesive 2000** applied by a notched trowel.
- 3.2 A 4mm thick prefabricated polyurethane rubber mat manufactured to Rebound Ace Sports' specifications for **Rebound Cricket Wickets**.
- 3.3 Two coats of **Mat Sealer**, applied by trowel to fully seal all pores of the rubber mat and all joints to provide a seamless surface. Apply one layer of Rebound Reinforcing at the batting crease into the 2nd coat of Mat Sealer PU.
- 3.4 One layer of **Rebound Reinforcing** encapsulated with one coat of **Rebound 8mm Tycoat** applied by a roller and allowed 24 hours to cure.
- 3.5 Minimum of two coats of **Rebound Flexible Coat** applied by a squeegee.
- 3.6 Minimum two coats of **Rebound Acrylic Cricket Wicket topcoat** applied by a Lambswool roller with 12 – 16mm nap

4. Linemarking

Rebound Linemarking AS applied by brush.

5. Coverage Rates

- 5.1 **Rebound Adhesive 2000** applied at a rate of 0.7-1.0 kg/m² dependant on the porosity of the surface, eg. Concrete 0.7 – 0.9 Kg/m² and Asphalt 0.9 - 1.2 Kg/m².
- 5.2 **Mat Sealer** applied at a rate of 0.6 - 0.8 Kg/m² for Mat Sealer PU .
- 5.3 **Rebound Ace 8mm Tycoat** applied at a rate of 0.5 - 0.6 Ltr/m² (0.5 – 0.6 kg/m²), to encapsulate **Rebound Reinforcing Mat**.
- 5.4 **Rebound Flexible Filler Coat** applied at a rate of 0.3 - 0.4 Ltr/m²/coat (0.5-0.6 kg/m²).
- 5.5 **Rebound Acrylic Cricket Wicket Topcoat** applied at a rate of 0.16 – 0.2 kg/m² in two (2) coats.
- 5.6 **Rebound Linemarking AS** as required

HEAD OFFICE: QUEENSLAND 15-21 Argon Street, Carole Park, Queensland 4300, Australia

☎ +61 7 37238800 Fax + 617 32714659

Email info@reboundace.com.au

www.reboundace.com.au